

Technical Specifications: **EXPO** (article code: 117)

	Unity measurements	Values and tolerances (*)
<b>Fiber Composition</b>	%	100% PROPITEX FR bacteriostatic
<b>Roll width</b>	cm	140 ± 2
<b>Weight per square meter</b>	g/mq	300 ± 15

	Values and tolerances (*)	
<b>Abrasion Resistance</b>	> 100000 Martindale cycles	
<b>Light Fastness (EN ISO 105-B02)</b>	5	
	Wet	Dry
<b>Fastness to Rubbing (EN ISO 105-X12)</b>	5	5

<b>Flammability</b>	1 IM UNI 9175 EN 1021-1:2006 EN 1021-2:2006 BS5852:2006 (CRIB5) California Technical Bulletin 117:2013
---------------------	--------------------------------------------------------------------------------------------------------------------

Maintenance symbols (\*\*)



DECLARATION OF CONFORMITY
<p>Does not hold Formic Aldehyde (Formaldehyde) standard UNI 8647            Reference to art. 1 par. 2 Decree 15/07/94 of the German Board of Health and its subsequent modifications; i.e. it does not contain azoic dyes that in reducing conditions develop amines (Law 28/07/94 n. 1670 - VERORDNUNG BGBL).            Content of heavy metals in the dyes within the tolerance limits (OEKO TEX STANDARD 100).            DPR 883 - fibrous composition (code). Legislative Decree 22/05/99 n. 194 - Official Gazette n° 146 of 24/06/99.</p> <p>(*) Tolerances suggested by the Technical Committee of A.E.I.H. (European Association of Garment Manufacturing Companies)            (**) In reference Italian Law n.126 (1991 – article 2), is necessary indicate to the consumer, limitation and particular caution to follow for normal use of the product.</p>