



CATAS S.p.A.
via Antica, 24/3
33048 San Giovanni al Natisone (UD)
+39 0432 747211 - lab@catas.com
www.catas.com

Testing site:
via Antica, 24/3
33048 San Giovanni al Natisone (UD)
tel. +39 0432 747211
lab@catas.com



LAB N° 0027 L
Membro degli MRA EA, IAF e ILAC

TEST REPORT

302521 / 1

Revision: 0
Date received: 17/12/20
Date of test: 11/01/21
Date of issue: 11/01/21

CHIOCCARELLO S.R.L.
VIALE DELL'INDUSTRIA, 4
36036 TORREBELVICINO (VI)
ITALIA

Sample name: Upholstered furniture covered with fabric "MADRID"

Assessment of the ignitability of upholstered furniture EN 1021:2014

The tests have been carried out in accordance with EN 1021-1:2014 "Ignition source: Smouldering cigarette" and EN 1021-2:2014 "Ignition source: Match flame equivalent" standards.

Description of tested materials as declared by the client

Cover

Fabric "MADRID" produced by Chioccarello S.r.l. Company, composition 100 % polypropylene FR, mass per unit area 230 g/m².

The exposed surface of the cover was tested, the cover has not been treated with a fire-retardant chemical.

Filling material (supplied by Laboratory as requested by the client)

Flame Retardant polyurethane foam (Crib 5), density 25 kg/m³.

Pre-treatment

The cover has not been subjected to the water soaking and drying procedure (Annex D).

Conditioning

At least 96 hours at 23 ± 2 °C temperature and 50 ± 5 % relative humidity.

This document is validated by digital signature and time stamping in accordance with the Italian laws and the European Directives which regulate the electronic signature systems.


Managing Director
Dr. Franco Bullian

The sample name and, when relevant, its description, are given by the orderer, and CATAS does not assume responsibility on this matter. This test report relates to the sample submitted for the test and no others. Additions, deletions or alterations are not permitted. This test report must always be reproduced in its entirety. Unless otherwise required by standards and technical specifications or agreed with the customer, any declarations of conformity made by CATAS are based on the comparison between results and reference values, where the confidence intervals of the measures are not taken into account. Unless otherwise stated, sampling is made by the customer; in this case the test results are referred to the sample as received.

page 1/3