



centro ricerche-sviluppo e laboratori prove  
 settori legno-arredo, ambiente e alimenti

CATAS S.p.A.  
 Iscr. Reg. Imprese Udine  
 nr. iscr. C.F. 01818850305  
 Reg. Impr. UD 20663  
 P. IVA : 01818850305  
 C.Soc. € 1.003.650,00 i.v.

Sede: Via Antica, 24/3  
 33048 S. Giovanni al Nat. UD  
 Tel. 0432.747211 r.a.  
 Fax 0432.747250  
<http://www.catas.com>  
 e-mail: [lab@catas.com](mailto:lab@catas.com)

Filiale:  
 Via Braille, 5  
 20851 Lissone MB  
 Tel. 039.464567  
 Fax 039.464565  
 e-mail: [lissone@catas.com](mailto:lissone@catas.com)



LAB N° 0027  
 Membro degli Accordi di Mutuo Riconoscimento  
 EA, IAF e ILAC

## TEST REPORT

### 141022 / 2

Date received: 07-05-12  
 Date of test: 15-05-12  
 Date of issue: 15-05-12

Sample name: "OFFICE"

MANIFATTURA LANE CHIOCCARELLO S.R.L.  
 VIA BRUNO BRANDELLERO, 9  
 36036 TORREBELVICINO (VI)  
 ITALIA

## Match flame equivalent test EN 1021-2:2006

### Description of tested materials as declared by the client

#### Outer cover

Fabric OFFICE produced by Manifattura Lane Chioccarello S.r.l. Company, composition 100 % polyester FR, mass per unit area 430 g/m<sup>2</sup>. The cover has not been treated with a fire-retardant chemical, the exposed surface of the cover was tested.

#### Filling material

Polyurethane foam T 40/RC 5E produced by Olmo Giuseppe S.p.a. Company, density 40 kg/m<sup>3</sup>.

#### Pre-treatment

The cover has not been subjected to the water soaking and drying procedure (Annex D) prior to being conditioned at least 24 hours at 23 ± 2 °C temperature and 50 ± 5 % relative humidity.

#### Test results

##### Non-ignition

##### Criteria of ignition

		Match flame equivalent			Comments
		1	2	3	
<b>Smouldering criteria</b>					
Unsafe escalating combustion	[3.1 a)]	No	No	No	-
Test assembly consumed	[3.1 b)]	No	No	No	-
Smoulders to extremities	[3.1 c)]	No	No	No	-
Smoulders through thickness	[3.1 c)]	No	No	No	-
Smoulders more than 1 h	[3.1 d)]	No	No	No	-
In final examination, presence of active smouldering	[3.1 e)]	No	No	No	-
<b>Flaming criteria</b>					
Unsafe escalating combustion	[3.2 a)]	No	No	No	-
Test assembly consumed	[3.2 b)]	No	No	No	-
Flames to extremities	[3.2 c)]	No	No	No	-
Flames through thickness	[3.2 c)]	No	No	No	-
Flames longer than 120 s	[3.2 d)]	No	No	No	-
Yes: does not meet requirement	No: meet requirement				

The uncertainties of measurement extended to a 95 % level of confidence (coverage factor k=2) are ± 0,2 seconds and ± 0,6 mm.

The above test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

*This document is validated by digital signature and time stamping in accordance with the Italian laws and the European Directives which regulate the electronic signature systems.*

*Managing Director*  
*M. Andrea Glavon*

The sample name and, when relevant, its description, are given by the orderer, and CATAS does not assume responsibility on this matter. This test report relates to the sample submitted for the test and no others. Additions, deletions or alterations are not permitted. This test report must always be reproduced in its entirety. Unless otherwise stated, sampling has been carried out by the orderer.

pag. 1/1