



Centro Tessile Serico Spa consortile
Via Castelnuovo, 3 - 22100 Como, Italia
Tel. +39 031 331211-120 Fax +39 031 3312180
Amministrazione/Contabilità
Tel. +39 0313312102-154
P.IVA - C.F. 02381270137
Capitale sociale euro 552.693,18 i.v.
mailbox@textilecomo.com
www.textilecomo.com

TEST REPORT

Report nr.: **1909804-003**
Report date: **06-dic-19**
Acceptance code: **1909804**
Acceptance date: **02-dic-19**
Start test date: **02-dic-19**
End test date: **06-dic-19**
References: **---**

Customer code: 08151

To:
CHIOCCARELLO SRL
via Viale dll'industria 4
36036 TORREBELVICINO (VI)

To the attention of:
sig. Matteo Chioccarello
Tel.nr: +39 0445 661651
Fax.nr.: .

Article description: **SALO'**
Declared composition: **100% Polyester FR**
End use: **Furnishing**
Typology: **Fabric**
Return: **No requested**
Sampling by customer

The results reported herein refer exclusively to the tested sample as received and do not involve any product approval by Centro Tessile Serico. This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory. The informations as Article Description, Declared Composition and Tipology listed above are data supplied by the Customer for which this Laboratory declines any responsibility.

TEST	M.U.	RESULTS
60384 VOLATILE ORGANIC COMPOUNDS (VOC)		
Method:	Internal Method	
Instrument:	GC-MSD headspace	
Volatile Organic Compounds:		
TEST CONDITIONS		
Technique: Headspace (HS) extraction and GC-Mass Analysis		
Oven: 100°C		
Loop: 110°C		
Transfer line: 135°C		
RESULTS		
Volatile organic compounds (VOC) are not detectable		

END OF TEST REPORT

Technical Head

Enrica Baldini