

Technical Specifications: **SUMMANO** (article code: 13)
FR flame retardant

	Unity measurements	Values and tolerances (*)
Fiber Composition	%	100% Polyester FR
Roll width	cm	140 ± 2
Weight per square meter	g/mq	250 ± 15

	Values and tolerances (*)	
Abrasion Resistance	> 100000 Martindale cycles	
Light Fastness (EN ISO 105-B02)	5	
	Wet	Dry
Fastness to Rubbing (EN ISO 105-X12)	5	5

Flammability	1 IM UNI 9175 EN 1021-1:2006 EN 1021-2:2006
---------------------	---

Maintenance symbols (**)



DECLARATION OF CONFORMITY

Does not hold Formic Aldehyde (Formaldehyde) standard UNI 8647
 Reference to art. 1 par. 2 Decree 15/07/94 of the German Board of Health and its subsequent modifications; i.e. it does not contain azoic dyes that in reducing conditions develop amines (Law 28/07/94 n. 1670 - VERORDNUNG BGBL).
 Content of heavy metals in the dyes within the tolerance limits (OEKO TEX STANDARD 100).
 DPR 883 - fibrous composition (code). Legislative Decree 22/05/99 n. 194 - Official Gazette n° 146 of 24/06/99.

(*) Tolerances suggested by the Technical Committee of A.E.I.H. (European Association of Garment Manufacturing Companies)

(**) In reference Italian Law n.126 (1991 – article 2), is necessary indicate to the consumer, limitation and particular caution to follow for normal use of the product.